

Imlay Canyon Gear								
Rope Water Absorption Testing								
<u>13-Jul-11</u>				<u>mm</u>	<u>m</u>	<u>kg</u>	<u>kg</u>	
						<u>Dry</u>	<u>Wet</u>	<u>% water</u>
<u>Rope Brand Model</u>	<u>Condition</u>	<u>Material Sheath</u>	<u>Material Core</u>	<u>Diam</u>	<u>Length</u>	<u>Weight</u>	<u>Weight</u>	<u>absorption</u>
Beal Joker DryCore Dynamic	Used Some	Nylon	Nylon	9.1	60	3.44	4.90	42.4%
Imlay Canyon Fire	Used Some	Polyester	Polyester	8.3	40	2.15	2.64	22.4%
Imlay Canyonero	Brand New	Polyester	Polyester	9.2	60	3.93	4.68	19.1%